

Barrier
Corporation9908 S.W. Tigard Street
Tigard, Oregon 97223
(503) 639-4192
FAX: (503) 684-1515

Typical sound absorption properties of 2 lb. per cubic foot polyester acoustical foam.

PRODUCT NUMBER	THICKNESS	NRC*	ABSORPTION COEFFICIENTS					
			FREQUENCY, HERTZ					
			125	250	500	1000	2000	4000
031035	1/2"	.31	.15	.21	.26	.17	.63	.65
031040	3/4"	.59	.16	.25	.40	.73	.98	.78
031031	1"	.63	.16	.25	.45	.84	.97	.87

*Noise reduction coefficient per ASTM C-384-58