

ATTN: KROOK



**CUSTOM GASKETS LTD.**  
**DIE-CUT TO YOUR SPECIFICATIONS**

975 WEST KENT AVE., VANCOUVER, BC V6P 6K8  
 PH: (604) 263-1426 FAX: (604) 263-7825

**PHYSICAL TEST REPORT**

CUSTOMER : I.G.M.		PRODUCT NAME: INDUSTRIAL RUBBER SHEETS		SIZE :	
P.O. NO: -		TEST DATE: 2005.07.21		REMARK: N.I. NEOPRENE 2PLY (340% NYLON FABRIC)	
TEST ITEM		UNIT	SPECIFICATION	TEST RESULT	REMARKS
BASIC STATE	HARDNESS(SHORE-A)	POINT	-	63	ASTM D 2240
	TENSILE STRENGTH	PSI	-	855	ASTM D 412
	ELONGATION	%	-	406	ASTM D 412
MATERIAL			NEOPRENE (BLACK)	NEOPRENE (BLACK)	

Following is the physical specifications for standard CI Neoprene. It is our technical data for CI Neoprene (IGM381) and please carefully check detail.

<< CI NEOPRENE >>

Durometer	Temperature range	Fabric type	ASTM Line Call Out	S.G.	Width	Thickness	Avg.Roll length
60±5 Duro	-20°F to +180°F	3.4 ounce Nylon	D2000-M2-BC607-A14-B14-F17	1.5	36" & 48"	1/32" to 1"	33ft to 66ft