

ATTN: Trevor

TYPICAL PHYSICAL PROPERTIES

open cell sponge rubber

PRODUCT	3110	3120	3130	3140	3150	6122NW	6110	6120	6130	3320	3330	5555	5600	ZX-870	ZX-981	ZX-875	9529	9639		
COLOR	BLACK	BLACK	BLACK	BLACK	BLACK	BLACK	BLACK	BLACK	BLACK	BLACK	BLACK	GRAY	GRAY	TAN	RED	DARK RED	BLACK			
POLYMER	NATURAL RUBBER					NATURAL/NEOPRENE RUBBER LOW DENSITY	NEOPRENE-MED OIL SWELL	EPDM	NATURAL RUBBER- EXPANSION JOINT	NATURAL RUBBER	NATURAL RUBBER	NATURAL RUBBER								
COMPRESSION DEFLECTION	SOFT	MED	MED FIRM	FIRM	EXTRA FIRM	MEDIUM	SOFT	MED	MED FIRM	SOFT	MED	VERY FIRM		MED FIRM	FIRM	EXTRA FIRM	MED	MED FIRM		
AT 25% - 181	2-5	5-10	10-16	16-22	22+	5-10	2-5	5-9	9-13	4-9	9-17			15-25	25-35	35+	5-10	10-15		
AT 50% - 781	—	—	—	—	—	—	—	—	—	—	—	50 MINIMUM		—	—	—	—	—		
COMPRESSION SET	15% MAXIMUM					15% MAXIMUM	50% MAX	40% MAX	15% MAXIMUM	15% MAXIMUM	AVERAGE	25	30	30	15% MAXIMUM					
AT 50% DEFLECTION AT 158°F																				
ACCELERATED AGEING - % CHANGE IN COMPRESSION DEFLECTION AT 158°F	±20%					±20%	±20%	±20%	±20%	±20%	±20%	±20%	±20%	±20%	±20%	±20%	±20%	±20%	±20%	±20%
TEMPERATURE RANGE	-20°F TO 160°F					-20°F TO 160°F	-20°F TO 115°F	-20°F TO 200°F	-20°F TO 160°F	-20°F TO 160°F	-20°F TO 160°F	-20°F TO 160°F	-20°F TO 160°F	-20°F TO 160°F	-20°F TO 160°F	-20°F TO 160°F	-20°F TO 160°F	-20°F TO 160°F	-20°F TO 160°F	-20°F TO 160°F
DENSITY-AVG POUND/SCUBIC FOOT	22	26	30	33	36	18	27	33	36	30	35	38	32	28	38	40	24	26		

NOTE: Information of a technical nature is based on laboratory tests which either Griswold Rubber Company, Inc. conducts or sends to an independent laboratory for testing for determination of uses as requested in writing by customer. Griswold Rubber Company, Inc. believes these to be reliable. However, Griswold Rubber Company, Inc. has no control over the application of the material to or part of the final product and therefore, Griswold Rubber Company, Inc. makes no express or implied warranty of result, fitness or merchantability. The customer should determine reliability for the end use or particular application.